

**P BFT5****SENSITIVE® BONDED H130**

Patent EUROJERSEY IT n. 1.239.906 EU n. 452.607

**STANDARD  
100****941273.0  
CENTROCOT**

www.oeko-tex.com

**COMPOSITION**

Front PA 75% EA 25% // Back PA 75% EA 25%

**INFORMATION**

Wt. g/l.m.:	470	+/- 6%	Wt. g/sq.m.:	347	+/- 6%
Width cm:	135	+ 3%	Width inch:	53	
Weight oz/sq.yd.:	10,20				
Custom Tariff:	60041000				

**TEST**

Dimension stability	Temp	Method/Technique	Width	Length
Domestic Wash.-Tumble Dry Low	40°C	ISO 6330 ISO 5077	+/-3%	-5%
Dry Cleaning- X care instruct.	30°C	ISO 3175 ISO 5077	+/-3%	-5%
Hoffman Press	110°C	DIN 53894	+/-3%	+/-3%

**Elasticity Dynamometer**

		Width	Toll. +/-	Length	Toll. +/-
% Elongation BS EN ISO 20932-1	15N	70,00	20 %	40,00	20 %
% Minimum Recovery @ 1 minute	15N	90		90	
% Elongation BS EN ISO 20932-1	35N	100,00	20 %	70,00	20 %
% Minimum Recovery @ 1 minute	35N	90		90	

**Other tests**

	Method/Technique	Value
Flammability CLASS	16CFR1610	1
pH of aqueous extract -KCl	ISO 3071	4,00/7,50
Bond strength/after 10 washes	ASTM D2724	>2
Abrasion Resistance	ISO 12947-2	20000
Pilling-Specim.fabric 7000revs	ISO12945-2	4/5
Snagging - Bean Bag 50 Revs	ASTM D5362	3.5
Snagging - Bean Bag 75 Revs	ASTM D5362	3.0
Bursting Strength / Ball Burst	ASTM D6797	>50
UPF / Original-Dry	AATCC 183 ASTM D6603	40+
UPF / Original-Wet	AATCC 183 ASTM D6603	40+
Drying Rate Test	AATCC 201	>1
Water Vapour Resistance Proc D	ASTM E96	>850
Appearance-10wash. X care inst	AATCC 124	>3
Wrinkle Recovery / Original	AATCC 128	>3

**OBSERVATIONS**

WAVE EFFECT DUE TO BONDING PROCESS UNEVEN ON THE ROLL, MORE VISIBLE ON LIGHT COLORS

**COMMENTS**

The manufacturer reserves the right to make technical changes to improve the quality of product at any time.  
Maximum fault rate: 1 in 20 metres.  
ISO 14001:2015 Certificate 0029426

**FABRIC CARE SYMBOLS**

Washing

DO NOT  
Bleaching

Ironing



Dry cleaning

Tumble  
Dry**NOTE**

- In order to confirm the reported data please contact Eurojersey S.p.A.
  - Producer reserves the right to modify the data.
  - SENSITIVE® is a registered trademark of Eurojersey S.p.A.
- The manufacturer reserves the right to make technical changes to improve the quality of product at any time.

**EUROJERSEY S.P.A.**

Via S. Giovanni Bosco, 260  
21042 Caronno Pertusella (Va) Italy  
Tel. +39 02 966541 Fax +39 02 9665 445  
[info@eurojersey.it](mailto:info@eurojersey.it) - [www.sensitivefabrics.it](http://www.sensitivefabrics.it)  
P.IVA 01879880126

